

## SLA Material Properties Table

Materials	Color	Tensile Strength/Mpa	Tensile Modulus/Mpa	Elongation/%
ABS-LIKE White	White	54.47	3300	9
ABS-LIKE Gray	Gray	39.98	2000	9
ABS-LIKE Black	Black	48.26	3000	5
ABS-LIKE Clear	Translucent/Clear	54.47	2600	6
PP-LIKE White	Translucent/White	34.47	1600	25
PC LIKE High Temp	Translucent/Clear	74.46	3503	7
PC LIKE Clear	Translucent/Amber	44.81	3902	1.5
Ceramic-Like High Temp	White	75.15	10500	1

*These figures are approximate and dependent on a number of factors, including but not limited to, machine and process parameters. The information provided is therefore not binding and not deemed to be certified. When performance is critical, also consider independent lab testing of additive materials or final parts.*

